

The orbital and charge ordering in $\text{Pr}_{1-x}\text{Ca}_x\text{MnO}_3$ ($x=0$ and 0.5) from the *ab initio* calculations

V.I.Anisimov, I.S.Elfinov, M.A.Korotin

Institute of Metal Physics, Russian Academy of Sciences, 620219 Ekaterinburg GSP-170, Russia

K.Terakura

*Joint Research Center for Atomic Technology, National Institute for Advanced Interdisciplinary
Research, 1-1-4 Higashi, Tsukuba, Ibaraki 305, Japan*

(February 1, 2008)

Abstract

The electronic structure of the doped manganites $\text{Pr}_{1-x}\text{Ca}_x\text{MnO}_3$ was calculated by the LSDA+U method which takes into account the local Coulomb interaction between d-electrons of transition metal ions. In contrast to the standard local spin density approximation (LSDA) no Jahn-Teller lattice distortions are needed to reproduce the experimentally observed orbital ordering in the undoped PrMnO_3 . The correct ground state : a charge and orbital ordered antiferromagnetic insulator, was obtained for $\text{Pr}_{1/2}\text{Ca}_{1/2}\text{MnO}_3$. The results are in good agreement with the neutron diffraction data.

I. INTRODUCTION

The doped rare earth manganites $\text{Re}_{1-x}\text{A}_x\text{MnO}_3$ (Re is a rare earth such as La and A is a divalent element such as Sr or Ca) due to their peculiar correlation between magnetism and conductivity have been extensively studied during 1950s and 60s [1]. The most thoroughly investigated was the $\text{La}_{1-x}\text{Sr}_x\text{MnO}_3$ system. Undoped ($x=0$), LaMnO_3 is an antiferromagnetic insulator. Upon doping with Sr, this perovskite oxide becomes a ferromagnetic metal;

the connection between metallicity and ferromagnetism was well explained by the double exchange hopping mechanism [2]. The discovery of colossal magnetoresistance phenomena in samples with Sr dopant densities in the $0.2 \leq x \leq 0.4$ regime [3] brought a revival of the interest to these systems.

The Mn^{+3} ion in the hole-undoped compound LaMnO_3 has the high-spin d^4 electron configuration $t_{2g}^3 e_{g\uparrow}^1$. The t_{2g} orbitals hybridize with O2p orbitals much more weakly than the e_g orbitals and can be regarded as forming the localized spin ($S=3/2$). In contrast to that, e_g orbitals, which have lobes directed to the neighboring oxygen atoms, hybridize strongly with O2p producing in the result rather broad bands. The strong exchange interaction with $t_{2g\uparrow}$ subshell leads to the splitting of the e_g band into unoccupied $e_{g\downarrow}$ and half-occupied $e_{g\uparrow}$ subbands. The half filled $e_{g\uparrow}$ subband is a typical example of the Jahn-Teller system, and, indeed, LaMnO_3 has an orthorhombic crystal structure [4] with distorted (elongated) MnO_6 octahedra. This cooperative Jahn-Teller effect is usually considered responsible for the opening of the gap in the half-filled $e_{g\uparrow}$ band and an insulator ground state of LaMnO_3 .

The orthorhombic crystal structure of LaMnO_3 ($Pbnm$ space group) can be described as a perovskite with two types of distortion from a cubic structure: 1) Tilting (rotation) of the MnO_6 octahedra, so that Mn-O-Mn angles become less than 180° , and 2) Jahn-Teller distortion of the octahedra, with one long Mn-O bond and two short bonds. With doping by Sr the orthorhombicity (the deviation of the values of the lattice parameters b and $c/\sqrt{2}$ from a) becomes smaller and for $x \geq 0.175$ the stable crystal structure at room temperature becomes rhombohedral, where only tilting of oxygen octahedra is present but all three Mn-O bonds are equal. Around the same value of the doping x , $\text{La}_{1-x}\text{Sr}_x\text{MnO}_3$ becomes metallic.

For Sr doping with $0.2 \leq x \leq 0.4$, $\text{La}_{1-x}\text{Sr}_x\text{MnO}_3$ is a ferromagnetic metal at low temperatures. However, as the temperature increases and approaches the Curie temperature T_c a sudden increase of the resistivity is observed [3]. As the temperature dependence of the resistivity $\rho(T)$ has typically semiconducting behavior ($d\rho/dT < 0$) above T_c , this increase in resistivity at around T_c is usually described as a metal-insulator transition. The colossal magnetoresistance effect happens when the temperature is close to T_c : the external magnetic

field leads to suppression of the resistivity increase or to shifting the metal-insulator transition to higher temperatures resulting in a very large negative value of $[\rho(H) - \rho(0)]/\rho(0)$.

The crucial point in the understanding of the effect of the colossal magnetoresistance is the nature of the metal-insulator transition with the temperature variation across T_c . It was shown [5] that the double exchange mechanism alone is not enough to explain such transition. Millis *et al.* [6] suggested local Jahn-Teller distortions (Jahn-Teller polarons) as a main mechanism causing localization. Their idea is that a E_{JT}/W ratio (E_{JT} is self-trapping Jahn-Teller polaron energy and W is effective band width) is close to the critical value in $\text{La}_{1-x}\text{Sr}_x\text{MnO}_3$ and as W decreases with destroying the ferromagnetic order above T_c (the effective hopping takes the maximum value for a parallel spin alignment), this ratio becomes larger than the critical value to result in polaron localization. Varma [7] argues that LaMnO_3 is not an insulator due to the Jahn-Teller distortion but is a Mott insulator and the Jahn-Teller distortion occurs parasitically. He explains localisation of the holes in the paramagnetic phase by spin polaron mechanism.

By replacing La with other trivalent ions with smaller ionic radius, the Mn-O-Mn bond angle becomes smaller and the e_g band width W is reduced to enhance the tendency to the carrier localization and lattice distortion. Variety of dramatic phenomena have been observed in (Pr, Nd, Sm)(Sr, Ca) MnO_3 systems. As one of such examples, we study $\text{Pr}_{1/2}\text{Ca}_{1/2}\text{MnO}_3$ in the present paper. This system has a very peculiar phase diagram [8,9]. At low temperature, it is an antiferromagnetic insulator with a charge ordering of Mn^{3+} and Mn^{4+} accompanied by an orbital ordering: the orbital ordering and spin ordering is of CE-type. Between T_N ($\simeq 180$ K) and T_{co} ($\simeq 240$ K), there is no long-range magnetic ordering but the system remains to be insulating because of the persistence of the charge ordering. Above T_{co} , it is a paramagnetic insulator.

The local spin density approximation (LSDA) [10] was used by several groups for theoretical investigation of the electronic structure of $\text{La}_{1-x}\text{Sr}_x\text{MnO}_3$ [11–13]. Those calculations have confirmed the importance of the Jahn-Teller distortion for correct description by the LSDA of the insulating antiferromagnetic ground state of the undoped LaMnO_3 , because

the calculations with an undistorted cubic perovskite crystal structure produce a half-filled metallic $e_{g\uparrow}$ band. However in order to address the charge and orbital order observed in doped manganites it is necessary to go beyond LSDA by including the intra d-shell Coulomb interaction (LSDA+U method [14–16]). Recently such an approach was used for treating the charge ordering in magnetite Fe_3O_4 , where LSDA gives a metallic uniform solution. The LSDA+U calculation gave a charge ordered insulator as the ground state of this compound [17]. In this paper we describe the results of the electronic structure calculation for $\text{Pr}_{1-x}\text{Ca}_x\text{MnO}_3$ for $x = 0$ and 0.5 in the LSDA+U approximation.

II. COMPUTATIONAL METHOD

The problem of the charge ordering cannot be treated properly by the standard LSDA because of the non-vanishing self-interaction. In contrast to the Hartree-Fock approximation, where the self-interaction is explicitly excluded for every orbital, in the LSDA it is canceled to a good approximation in the total energy, but rather poorly in the local one-electron potentials, which are orbital-independent. The spurious self-interaction present in the LSDA leads to an increase in the Coulomb interaction when the distribution of the electron charge deviates from the uniform one. This effect can be illustrated in the following way. If we consider the system having less than one electron per site in the partially filled electronic subshell (for example e_g -electrons in $\text{La}_{1-x}\text{Sr}_x\text{MnO}_3$) then the potential which this electron feels at some site must not depend on the orbital occupancy of this particular site, as the electron does not interact with itself. However, as the LSDA potential is a functional of the electron density only, increasing the electron density at one site and decreasing it at another one, with a formation of the charge ordering, will lead to an increase of the potential at the first site and a decrease at the second one. As a result, in the self-consistency loops, the charge distribution will return to the uniform density. In order to cure this deficiency, it is necessary to remove the self-interaction. The LSDA+U method [14,16] is one of the practical methods to solve the self-interaction problem.

Let us introduce the d-orbitals occupation matrix defined by:

$$n_{mm'}^\sigma = -\frac{1}{\pi} \int^{E_F} \text{Im} G_{inlm, inlm'}^\sigma(E) dE, \quad (1)$$

where $G_{inlm, inlm'}^\sigma(E) = \langle inlm\sigma | (E - \widehat{H})^{-1} | inlm'\sigma \rangle$ are the elements of the Green function matrix (i : index of atom site, nl : main and orbital quantum numbers (for example $3d$), m : index of a particular d -orbital and σ : spin projection index). In terms of the elements of this occupation matrix $\{n^\sigma\}$, the LSDA+U functional [16] is defined as follows:

$$E^{LSDA+U}[\rho^\sigma(\mathbf{r}), \{n^\sigma\}] = E^{LSDA}[\rho^\sigma(\mathbf{r})] + E^U[\{n^\sigma\}] - E_{dc}[\{n^\sigma\}] \quad (2)$$

Where $\rho^\sigma(\mathbf{r})$ is the charge density for spin- σ electrons and $E^{LSDA}[\rho^\sigma(\mathbf{r})]$ is the standard LSDA (Local Spin-Density Approximation) functional. $E^U[\{n^\sigma\}]$ is the Hartree-Fock type electron-electron interaction energy given by

$$E^U[\{n\}] = \frac{1}{2} \sum_{\{m\}, \sigma} \{ \langle m, m'' | V_{ee} | m', m''' \rangle n_{mm'}^\sigma n_{m''m'''}^{-\sigma} - (\langle m, m'' | V_{ee} | m', m''' \rangle - \langle m, m'' | V_{ee} | m''', m' \rangle) n_{mm'}^\sigma n_{m''m'''}^\sigma \}, \quad (3)$$

where V_{ee} is the screened Coulomb interaction among the nl electrons. Finally, the last term in Eq.(2) corrects for double counting and is given by

$$E_{dc}[\{n^\sigma\}] = \frac{1}{2} U N(N-1) - \frac{1}{2} J [N^\uparrow(N^\uparrow-1) + N^\downarrow(N^\downarrow-1)], \quad (4)$$

where $N^\sigma = \text{Tr}(n_{mm'}^\sigma)$ and $N = N^\uparrow + N^\downarrow$. U and J are screened Coulomb and exchange parameters [18,19].

In addition to the usual LSDA potential, the variation of the functional (2) gives an effective single-particle potential to be used in the single-particle Hamiltonian :

$$\widehat{H} = \widehat{H}_{LSDA} + \sum_{mm'} | inlm\sigma \rangle V_{mm'}^\sigma \langle inlm'\sigma | \quad (5)$$

$$\begin{aligned}
V_{mm'}^\sigma &= \sum_{m''m'''} \{ \langle m, m'' | V_{ee} | m', m''' \rangle n_{m''m'''}^{-\sigma} \\
&+ (\langle m, m'' | V_{ee} | m', m''' \rangle - \langle m, m'' | V_{ee} | m''', m' \rangle) n_{m''m'''}^\sigma \}
\end{aligned} \tag{6}$$

$$-U(N - \frac{1}{2}) + J(N^\sigma - \frac{1}{2}).$$

The matrix elements of the screened Coulomb interaction V_{ee} can be expressed in terms of complex spherical harmonics and effective Slater integrals F^k [20] as

$$\langle m, m'' | V_{ee} | m', m''' \rangle = \sum_k a_k(m, m', m'', m''') F^k, \tag{7}$$

where $0 \leq k \leq 2l$ and

$$a_k(m, m', m'', m''') = \frac{4\pi}{2k+1} \sum_{q=-k}^k \langle lm | Y_{kq} | lm' \rangle \langle lm'' | Y_{kq}^* | lm''' \rangle$$

For d-electrons one needs F^0, F^2 and F^4 and these can be linked to the Coulomb- and Stoner parameters U and J obtained by the LSDA-supercell procedures [18,19] via $U = F^0$ and $J = (F^2 + F^4)/14$ with the ratio F^2/F^4 being to a good accuracy a constant ~ 0.625 for the 3d elements [15,21].

The LSDA+U approximation was realized in the framework of the linear muffin-tin orbital method in the atomic sphere approximation (LMTO-ASA) [22]. The values of $U=7.9$ eV and $J=0.9$ eV were used as obtained from the constrained LSDA supercell calculations.

III. RESULTS AND DISCUSSION

As a first step the electronic structure of the undoped PrMnO_3 was calculated. This compound has practically the same properties as LaMnO_3 . The only difference is that due to the smaller ionic radius of Pr ion compared with that of La ion, the tilting of the oxygen octahedra in orthorhombic $Pbnm$ crystal structure is stronger, resulting in smaller effective $e_g - e_g$ hopping between Mn atoms and narrower band width.

The crystal structure of the doped $\text{Pr}_{1-x}\text{Ca}_x\text{MnO}_3$ does not show transition to the rhombohedral symmetry, as it is the case for $\text{La}_{1-x}\text{Sr}_x\text{MnO}_3$, preserving the orthorhombic $Pbnm$ space group [8]. However the values of the lattice parameters a, b and $c/\sqrt{2}$ for $x=0.5$ are so close that it can be called a pseudocubic structure. In this structure only the tilting of the oxygen octahedra is present, but octahedra themselves are not Jahn-Teller distorted as in the undoped crystal structure. In order to study effects of the orbital polarization purely due to the intrashell d-d Coulomb interaction without any influence of the Jahn-Teller lattice distortion the calculation for the undoped PrMnO_3 was performed with the crystal structure parameters corresponding to $\text{Pr}_{1/2}\text{Ca}_{1/2}\text{MnO}_3$.

Kugel and Khomskii [23] demonstrated for a wide range of Jahn-Teller magnetic compounds that the exchange mechanism (caused by an interplay between on-site Coulomb interaction U and intersite hopping t) by itself, without taking Jahn-Teller distortions into consideration, is able to give a correct picture of the spin and orbital ordering. In this case the change in the lattice structure (the structural transition) is a secondary effect. One may say that the system shows the "Jahn-Teller ordering" without the "Jahn-Teller interaction". Actually an exchange mechanism acts jointly with the Jahn-Teller and the quadrupole mechanisms. It is quite difficult to determine just which mechanism will be predominant in each specific case due to complexity of the real compound. One of the possible ways to answer this question in the frame of *ab-initio* band structure calculations is to use a crystal structure excluding distortions caused by the Jahn-Teller interaction.

Such kind of approach was used for the cooperative Jahn-Teller system KCuF_3 [16]. It also has the perovskite crystal structure, but there is no tilting of the CuF_6 octahedra and all Cu-F-Cu angles are equal to 180° . Divalent copper ion in this compound has a d^9 configuration $(t_{2g\uparrow}^3 t_{2g\downarrow}^3 e_{g\uparrow}^2 e_{g\downarrow}^1)$ known to be a Jahn-Teller ion, and, indeed, the Jahn-Teller distortion is observed in the form of the elongated CuF_6 octahedra with long axes alternatively along a and b axes in the ab -plane. Kugel and Khomskii [23] showed that a simple Hubbard model type calculation in a mean-field approximation without taking into account the electron-phonon interaction could predict the orbital ordering (alternating $3x^2 - r^2$ and

$3y^2 - r^2$ Cu3d-orbitals for electrons or $x^2 - z^2$ and $y^2 - z^2$ orbitals for holes) corresponding to the symmetry of the experimentally observed lattice distortions.

The LSDA+U functional (eq.2) has a definite important improvement upon the LSDA: explicit cancellation of the self-interaction and the proper description of the lowering of Coulomb interaction energy with development of the orbital polarization. The functional (eq.2) is also rotationally invariant (the total energy does not change with the unitary transformation of the d-orbital basis set $|m\rangle$), meaning that if the local coordinate system (and, correspondingly d-orbital basis set $|m\rangle$) was chosen inappropriately for describing the resulting orbital polarisation, the unitary transformation which diagonalizes the non-diagonal occupation matrix $n_{mm'}^\sigma$ (eq.1) will give a proper orbital basis set.

The LSDA+U calculation for KCuF_3 [16] in *cubic* perovskite crystal structure gave results fully confirming Kugel-Khomskii's prediction - alternating $3x^2 - r^2$ and $3y^2 - r^2$ orbital order. Moreover, it was not just the lowest total energy configuration among many possible stationary configurations as in the model calculation [23], but the *only one stable solution*. The lattice relaxation to minimize the total energy is in good agreement with experimental data. Note that the standard LSDA did not show the lattice instability with respect to the Jahn-Teller distortion in KCuF_3 . We would like to emphasize that the orbital polarization caused by the d-d Coulomb interactions practically did not change with the lattice distortion [24].

The use of the crystal structure parameters corresponding to $\text{Pr}_{1/2}\text{Ca}_{1/2}\text{MnO}_3$ (with undistorted oxygen octahedra) for PrMnO_3 may correspond to the use of the cubic perovskite crystal structure for KCuF_3 . However, for PrMnO_3 , we have to take into account the tilting of MnO_6 octahedra (present in $\text{Pr}_{1/2}\text{Ca}_{1/2}\text{MnO}_3$ structure), which is essential for the proper description of the reduction in the effective $e_g - e_g$ hopping due to the bending of the Mn-O-Mn bond. The LSDA+U calculation with the experimental A-type antiferromagnetic spin alignment resulted in a non-diagonal occupation matrix for spin density (for the e_g subspace ($3z^2 - r^2$ and $x^2 - y^2$ orbitals) of one particular Mn atom):

$$n_{mm'}^\uparrow - n_{mm'}^\downarrow = \begin{pmatrix} 0.31 & 0.22 \\ 0.22 & 0.58 \end{pmatrix} \quad (8)$$

The diagonalization of this matrix gives two new $e_{g\uparrow}$ orbitals: $\phi_1 = 3y^2 - r^2$ with occupancy 0.71 and $\phi_2 = z^2 - x^2$ with occupancy 0.18. For the second type of Mn atom ϕ_1 and ϕ_2 orbitals can be obtained by transposition of x and y .

The resulting orbital order can be presented graphically by plotting the angle distribution of the e_g -electron spin density:

$$\rho(\theta, \phi) = \sum_{mm'} (n_{mm'}^\uparrow - n_{mm'}^\downarrow) Y_m(\theta, \phi) Y_{m'}(\theta, \phi) \quad (9)$$

As a Mn^{+3} ion has formally only one electron in partially filled $e_{g\uparrow}$ subshell, the e_g -spin density must correspond to the density of this electron (Fig.1).

The plot of Fig.1 and the form of the ϕ_1 and ϕ_2 orbitals diagonalizing the spin density occupation matrix show that the orbital order obtained in our LSDA+U calculations for PrMnO_3 is of the same symmetry as the one in KCuF_3 . The "parasitical" lattice distortion, which one could expect from such orbital ordering: elongation of MnO_6 octahedra in the direction of the lobes of ϕ_1 orbitals, will reproduce the experimentally observed Jahn-Teller lattice distortion.

The orbital polarization is far from being 100%, the difference in the occupancy of ϕ_1 and ϕ_2 orbitals is only 0.53. The reason for this is the strong hybridization of $e_{g\uparrow}$ -orbitals with oxygen 2p-orbitals. In Fig.2, the total and partial densities of states (DOS) for PrMnO_3 are shown (for e_g -electrons DOS projected on ϕ_1 and ϕ_2 orbitals are also presented).

The electronic structure obtained in our LSDA+U calculation is semiconducting with a band gap of 0.5 eV. Note that the standard LSDA needs the Jahn-Teller distorted crystal structure to reproduce the non-metallic ground state. The $e_{g\uparrow}$ -band is split by this gap into two subbands: the occupied one with the predominantly ϕ_1 character, and the empty one with the ϕ_2 character. However there is significant admixture of ϕ_2 in the occupied subband and ϕ_1 in the empty one.

After checking that our calculation scheme gives a proper orbital order in the undoped PrMnO_3 , we applied it to $\text{Pr}_{1/2}\text{Ca}_{1/2}\text{MnO}_3$. In order to treat the experimentally observed CE-type of antiferromagnetism it was necessary to quadruple the $Pbnm$ -type unit cell and the supercell had 16 formula units. The distribution of the Pr and Ca atoms in the lattice was chosen according to a model where all Pr ions have only Ca as their nearest neighbors in the lanthanide sublattice. We did not impose any symmetry restrictions in our calculation, the integration in the reciprocal space being performed for the whole Brillouin zone, and the self-consistency iteration was started from a uniform distribution of e_g -electrons over both e_g -orbitals of all Mn atoms.

The result of the self-consistent calculation was a charge and orbital ordered insulator. The e_g -electron spin-density-plot calculated by eq.9 is presented in Fig.3. This is in a striking agreement with the orbital order derived in [8] from the neutron diffraction measurements (Fig.4). The unexpected result is that the total number of d-electrons at all types of Mn sites are nearly equal (4.99 and 5.01), so that formally Mn^{4+} ions (in the Fig.3 the ones with symmetric in-plane density distribution) and Mn^{3+} ions (the ones with the density strongly anisotropic) have nearly the same number of 3d-electrons. However the difference in the magnetic moment values is more pronounced : $3.34\mu_B$ for Mn^{4+} and $3.44\mu_B$ for Mn^{3+} .

IV. CONCLUSION

The results of our LSDA+U calculations for $\text{Pr}_{1-x}\text{Ca}_x\text{MnO}_3$ demonstrate that taking into account the Coulomb interaction inside the d-shell of Mn together with the intersite hopping is enough to reproduce not only the orbital order present in the undoped manganites, but also the localization and ordering of the holes in the doped materials. Naturally the lattice relaxation (Jahn-Teller and polaron lattice distortions) will significantly renormalize the total energies, gap values, charge disproportion and magnetic moments. However it seems that the symmetry of the ordered state can be obtained without explicitly including the electron-lattice interactions. This is in clear contrast to the standard LSDA where energy

band splitting and orbital polarization appear only as results of the Jahn-Teller crystal structure distortion.

V. ACKNOWLEDGMENTS

V.I.A. and M.A.K. acknowledge the NAIR Guest Research Program. The present work is supported partly by Russian Foundation for Basic Research (RFBR grant 96-02-16167), New Energy and Industrial Development Organization in Japan and also by a Grant-in-Aid for Scientific Research in the priority area "Anomalous Metallic States Near the Mott Transition" from the Ministry of Education, Science and Culture of Japan.

REFERENCES

- [1] G. H. Jonker and J. H. van Santen, *Physica (Amsterdam)* **16**, 337 (1950); J. H. van Santen and G. H. Jonker, *Physica (Amsterdam)* **16**, 599 (1950).
- [2] C. Zener, *Phys. Rev.* **82**, 403 (1951); P. W. Anderson and H. Hasegawa, *Phys. Rev.* **100**, 675 (1955); P. G. de Gennes, *Phys. Rev.* **118**, 141 (1960).
- [3] R. M. Kusters, J. Singleton, D. A. Keen, R. McGreevy and W. Hayes, *Physica (Amsterdam)* **155B**, 362 (1989); A. Urushibara, Y. Moritomo, T. Arima, A. Asamitsu, G. Kido and Y. Tokura, *Phys. Rev.B* **51**, 14103 (1995).
- [4] J. B. A. A. Elemans, B. van Laar, K. R. van der Veen and B. O. Loopstra, *J. Solid State Chem.* **3**, 238 (1971).
- [5] A. J. Millis, P. B. Littlewood and B. Shraiman, *Phys. Rev. Lett.* **74**, 5144 (1995).
- [6] A. J. Millis, B. Shraiman and R. Mueller, *Phys. Rev. Lett.* **77**, 175 (1996).
- [7] C. M. Varma, preprint.
- [8] Z. Jirak, S. Krupicka, V. Nekvasil, E. Pollert, G. Villeneuve and F. Zounova, *J. Magn. Magn. Mater.* **15-18**, 519 (1980); Z. Jirak, S. Krupicka, Z. Simsa, M. Dlouha and Z. Vratislav, *ibid.* **53**, 153 (1985).
- [9] Y. Tomioka, A. Asamitsu, H. Kuwahara, Y. Moritomo and Y. Tokura, *Phys. Rev.* **B53**, R1689 (1996).
- [10] P. Hohenberg and W. Kohn, *Phys. Rev.* **136**, B864 (1964); W. Kohn and L. J. Sham, *ibid.* **140**, A1133 (1965).
- [11] N. Hamada, H. Sawada and K. Terakura, in *Spectroscopy of Mott Insulators and Correlated Metals*, edited by A. Fujimori and Y. Tokura (Springer-Verlag, Berlin, 1995), pp.95-105.
- [12] W. Pickett and D. Singh, *Phys. Rev.B* **53**, 1146 (1996).

- [13] S. Satpathy, Z. Popovic and Ph. Vukajlovic, Phys. Rev. Lett. **76**, 960 (1996).
- [14] V. I. Anisimov, J. Zaanen and O. K. Andersen, Phys. Rev. B **44**, 943 (1991).
- [15] V. I. Anisimov, I. V. Solovyev, M. A. Korotin, M. T. Czyzyk and G. A. Sawatzky, Phys.Rev. B **48**, 16929 (1993).
- [16] A. I. Lichtenstein, J. Zaanen and V. I. Anisimov, Phys. Rev.B**52**, R5467, (1995).
- [17] V. I. Anisimov, I. S. Elfimov, N. Hamada and K. Terakura, Phys.Rev.B **54**, 3847 (1996)
- [18] O. Gunnarsson, O. K. Andersen, O. Jepsen and J.Zaanen, Phys. Rev. B**39**, 1708 (1989).
- [19] V. I. Anisimov and O. Gunnarson, Phys. Rev. B **43**, 7570 (1991).
- [20] B. R. Judd, 'Operator techniques in atomic spectroscopy', McGrow-Hill,New York,1963.
- [21] F. M. F. de Groot, J. C. Fuggle, B. T. Thole and G. A. Sawatzky, Phys. Rev. B **42**, 5459 (1990).
- [22] O. K. Andersen, Phys. Rev. B **12**, 3060 (1975).
- [23] K. I. Kugel and D. I. Khomskii, Usp. Fiz. Nauk. **136**, 621(1982) [Sov. Phys. -Usp. **25**, 231(1982)].
- [24] The LSDA works much better in LaMnO_3 and perhaps also in PrMnO_3 than in KCuF_3 . In the latter case, the LSDA does not give even a stable antiferromagnetic state. However, in LaMnO_3 and PrMnO_3 , the antiferromagnetic state can be obtained by LSDA. Our recent calculation (H. Sawada, et al.) for LaMnO_3 reproduces about 50% of the experimental Jahn-Teller distortion by the theoretical structural optimization for experimental lattice parameters.

Figure captions

Fig. 1. The calculated angle distribution of the $e_{g\uparrow}$ -electron spin density in PrMnO_3 .

Fig. 2. The total and partial densities of states (DOS) from the result of LSDA+U calculation of PrMnO_3 . a) Total DOS per unit cell (4 formula units); b) Partial e_g DOS of Mn. Solid lines are for the ϕ_1 -projected DOS, and dashed lines for the ϕ_2 -projected DOS with ϕ_1 and ϕ_2 -orbitals diagonalizing the occupation matrix.; c) and d) Partial DOS for two types of oxygen orbitals.

Fig. 3. The calculated angle distribution of the $e_{g\uparrow}$ -electron spin density in $\text{Pr}_{1/2}\text{Ca}_{1/2}\text{MnO}_3$.

Fig. 4. The scheme of the spin, charge and orbital order in $\text{Pr}_{1/2}\text{Ca}_{1/2}\text{MnO}_3$ deduced from the neutron diffraction data [8]. The open circles with the lobe of the e_g electron density distribution denote Mn^{3+} and the filled circles Mn^{4+} . The arrows denote the magnetic moments.







